

Deckshield UV

A 2-component, coloured, UV light stable, polyurethane coating.

Used as part of the Deckshield system to provide a UV light stable finish.

Environment & Health

Deckshield UV contains solvent, ensure adequate ventilation and/or extraction. Follow the appropriate Occupational Health and Safety guidelines applicable to the location where the application is undertaken.

For more information, please refer to the safety datasheets for the individual components.

Ratio of Components

The product is supplied in full units as A+B. Do not split the compounds/components as this may jeopardise the end result.

Add all of Hardener B to Base A. Mix with slow speed drill and helical spinner, taking care not to entrain air.

Application Temperature

The recommended substrate temperature is 15 - 30°C, but no less than 5°C.

The temperature of the substrate should exceed the "dew point" by 3°C during application and hardening.

Temperatures should not fall below 5°C in the 24hrs after application.

Application Time/Pot Life

Ready-mixed product should be used within 40 minutes at a temperature of 20°C.

At higher temperatures the application time is shorter.

Technical Profile*

COLOURS

See the system data sheets for Deckshield.

SOLIDS CONTENT

Approx. 60 % (by weight)

FINISH

Gloss

DENSITY

A+B approx. 1.2 kg/l.

Curing time (@200C)

Tack free after 8 hours, can be overcoated after 16 hours.

Can be walked on after 16 hours.

Maximum overcoat time 24 hours.

The product is fully hardened after 5 - 7 days.

Ambient humidity should be between 30 and 80% RH during application and cure. High humidity in the early stages of cure can result in white, matt surfaces (blooming). Do not cover or wash within the first 24 hours of curing.

Storage

12 months in unopened pack.

Storage temperature between 5°C and 30°C.

Packaging

The product is delivered A+B in the following packs.

Unit		Base A	Hardener B
5 kg	(4.17 litres)	8.0 kg	2.0 kg