# CHRYSO<sup>®</sup>Delta G555

# New Generation Water Reducing cum Accelerating Admixture



# Description

CHRYSO®Delta G555 is a new generation multi range liquid accelerator based on modified polycarboxylic ether .

#### Indicative characteristics

- Form
- orm : Light Amber Liquid
- Specific Gravity : 1.07 ± 0.02
- Air entrainment  $: \le 1.5$  % over control mix.
- pH
- : ≥6
- Chloride Content : Nil, as per BS 5075 (Part-I)
- Compatibility : OPC, PSC, PPC, and SRC

## **ADVANTAGES :**

Thanks to specifically designed molecular structure, CHRYSO<sup>®</sup> Delta G555 has a great flexibility; thanks to its large scale of dosage, it can be used in great range of concrete with desired setting time & hardening of concrete mix, thereby achieving higher early strength.

It allows early remolding of shutters/ formwork. It is strongly recommended for reinforced precast concrete. It is excellent for cold weather concreting.

Depending on dosage, a relative increase of mechanical strength is observed at 24 hours & is a great advantage over Old generation available Admixtures in the market.

For any mix, keeping the cement consumption and workability constant, substantial reduction in the amount of mixing water (up to 20 %) can be achieved, to produce concrete of high compressive strength. Alternatively, for the same concrete mix, keeping everything else constant, *a definite economy in cement content*, around 10% to 20%, can be achieved.

#### Precautions

Not to be stored at high temperatures for long periods. Should be protected from frost. It is Non-toxic and formulated from chemicals which present no fire or health hazards.

# Method of use

Dosage: Optimum dosage can only be established after trials, taking into account the rheological characteristics and the required mechanical performances. Rate of addition is generally in the range of 0.5 -2.0 % by wt of cementitious material.

For maximum dispersion throughout the mix, CHRYSO®Delta G555 should be added to the mixing water only. Should the product be added to fresh concrete, into the mixing truck, it is necessary to mix at high speed, and then at low speed (with a minimum 3 minutes at each speed)

#### Guideline Followed :

IS: 9103-2007 and ASTM C-494-2010(Type-E).

**Shelf Life:** If stored in unopened containers at normal ambient temperatures, a shelf-life of approximately 6 months.

## Packaging

225 Kgs Barrel & bulk in 10 KL tanker

# Safety

Before use, refer to the Material Safety Data Sheet. The MSDS is available on www.chryso.com.

The information contained in this technical data sheet is given to the best of our knowledge and the results from extensive testing in order to remain as objective as possible. However, it cannot, in any case be considered as a warranty involving our liability in case of misuse or any different use of our products from the "Application" paragraph of this technical data sheet. Some application tests should be carried out before using the product to ensure that the methods of use and conditions of application of the product are satisfactory. Our technical assistance is at the disposal of the users. Consult the latest update of the technical data sheet on our website **www.chryso.com** 



CHRYSO India Private Limited | Registered & Corporate Office : Plot No. D -30/7, TTC Industrial Area, M.I.D.C. Turbhe, Navi Mumbai – 400705. Maharashtra, INDIA. Tel : +91 22 27685991/2